

Lapeyre Industrial Sands-San Juan Capistrano, Orange County

Product Data Sheet #60 D Industrial Sand

#60 D Industrial Sand

| Typical Physical Properties | | | |
|-----------------------------|-------------------------|---------|--|
| Color: | Light Gray | | |
| Grain Shape: | Sub-angular | | |
| Hardness: | 6.5 | | |
| Moisture Content,(% by Wt): | <0.1 (kiln dried) | | |
| Bulk Density : | 89 lbs/ft (1426 kg/m3) | | |
| Specific Gravity: | 2.6 | | |
| Effective Size: | 0-10-0-20 | | |
| Uniformity Coefficient: | 1.50-1.70 | | |
| Турі | cal Particle Size Distr | ibution | |
| US Sieve No. | % Retained on Sieve | Range | |
| 40 | 1 | 0-1 | |
| 50 | 8 | 0-20 | |
| 70 | 37 | 30-60 | |
| 100 | 41 | 20-50 | |
| 140 | 11 | 5-20 | |
| 200 | 1 | 0-5 | |
| Disclaimer: | | | |

The information presented in this Product Data Sheet lists typical properties of the described product. By this Product Data Sheet, P.W. Gillibrand Co., Inc. makes no warranty, expressed or implied, of fitness for any purpose.

Warning:

This product contains crystalline silica (Quartz), known to the State of California to cause cancer. For additional information on the potential health effects of crystalline silica, please see the P.W. Gillibrand Co., Inc. Safety Data Sheet (SDS).

Phone N. 949 728 0171

PO. Box 1019, 4537 Ish Drive, Simi Valley, CA 93062-1019 Ph: 805 526 2195 Fax: 805 522 4031

www.pwgillibrand.com